

Cont  
A3  
1. (Amended) A steel excellent in abrasion resistance [essentially] consisting essentially of 8.0-35.0 wt.% Cr, 0.05-1.20 wt.% C, 0.05-3.0 wt.% at least one of Ti, Nb, Zr, V and W, [and] the balance being essentially Fe and having the structure that a total amount of Ti, Nb, Zr, V and/or W carbide [precipitations] precipitates distributed in a steel matrix is adjusted to 0.1 wt.% or more.

Cancel claim 2.

Add new claim 3 as follows:

3. An abrasion-resistant steel consisting essentially of:  
8.0 to 35.0 wt.% Cr;  
0.05 to 1.20 wt.% C;  
at least one of 0.05 to 1 wt.% Ti and 0.05 to 1.50 wt.% Nb wherein an aggregate of Ti + Nb is 0.50 to 2.0 wt.%;  
optionally one or more metals selected from the group consisting of Zr, Al and W in an aggregate summed with Ti + Nb up to 3.0 wt.%;  
further optionally one or more of 0.2-5.0 wt.% Ni, 0.1-3.0 wt.% Mo and 0.2-3.0 wt.% Cu; and  
with the balance being essentially Fe,  
wherein said Ti, Nb, Zr, V and/or W are present in the form of carbide precipitates distributed within a steel matrix in an amount of at least 0.1 wt.%.  
A4

IN THE ABSTRACT:

Please replace the current Abstract with the following substitute Abstract, which is also attached as a separate page. A marked-up version of the substitute Abstract is also attached hereto.

A5  
--An abrasion resistant steel consisting essentially of 8.0-35.0 wt.% Cr, 0.05-1.20 wt.% C, 0.05-3.0 wt.% at least one of Ti, Nb, Zr, V and W and the balance being